


Product Specification MODEL **NH-AA-3S1P-1M**

(Type) : AA1000mAh

Specifications of single cell

Nominal voltage			1.2V	
			1C Discharge	
Cap	pacity	Minimum	56min	
, ,		Typical	58min	
			mm	
Dimor		Diameter	14.5 ^{-0.7}	
Dimer	ISIONS	Height	49.0 ^{-1.0}	
			gram	
We	ight(Approxir	mately)	16.0	
			35mΩ(Max)	
Internal I	mpedance	At 1000 Hz		
		Standard	100mA(0.1C)×16hrs	
Charge		Rapid	1000mA(1.0C)×1.	
	0		2भूती	
rre t	emperature Charge	standard	0°℃ to 40°℃	
Ambient mperature		Rapid	0° C to 40° C	
te ,	Discharge		-20℃ to 50℃	
	Storage		-20℃ to 30℃	

PVC (Dimensions with tube)



Note:

1.

Nominal capacity, rated at 0.2C 20°C.

2.


Average capacity, for reference only.


3.

Weight and internal impedance are For reference.

4.

Standard according as IEC of test cycle life $\,{}^\circ$





The specification is suitable for the performance of NI-MH rechargeable battery produced

2. MODEL

1.

AA1000mAh 3.6V

3. APPEARANCE

There shall be no such details as discoloration or electrolyte leakage or 0 voltage.

4. RATINGS

Description	Unit	Specification	Condition	
Nominal Voltage	V	3.6	Unit pack	
Typical Capacity	min	308	Standard Charge/Discharge	
Nominal Capacity	mAh	1000	Standard Charge/Discharge	
Minimum Capacity	min	294	StandardCharge/ Discharge	
	mA	100(0.1C)	Ta=0~40 ℃	
Standard Charge	hour	16	(see note 1)	
	mA	200(0.2C)~1000(1.0C)	-∆V=10mV/pack	
		With charge termination control	Timer cutoff=110%input capacity Temp. cutoff=40~45℃	
Fast Charge	hour	6.0 approx.(0.2C) 1.1 approx(1.0C)	dT/dt=0.8℃/min(0.5 to 1.0C); 0.8~1℃/min(1C)	
Trickle Charge	mA	20(0.02C)~40(0.05C)	Ta=0~40°C (see note 1)	
Discharge Cut-off Voltage	V	3.0	Unit pack	
Maximum Discharging Current	mA	3000(3.0C)momentary	Ta =0∼50°C 2.4v cut off	
Storage Temperature	°C	-20~+25(within 1 year) -20~+30(within 3 month) -20~+40(within 1 month) -20~+50(within 1 week)	*	
Typical Weight	g	54	*	

PERFORMANCE

Before proceed the following tests, the cells should be discharged at 0.2C to 1.0V cutoff. Unless otherwise stated, tests should be done within one month of delivery under the following conditions:

Ambient temperature: 20°C±5°C

Relative Humidity: $65 \pm 20\%$

Note Standard Charge/Discharge Conditions:

Charge: 100mA(0.1C)×16hrs

Discharge: 200mA(0.2C) to 1.0V/cell

Test	Unit	Specification	Condition	Remarks
Capacity	min	≥294	Standard Charge / Discharge	Up to 3 cycles are allowed
Open circuit Voltage (OCV)	V	≥3.6	Within 1 hr after standard charge	Unit pack
Internal Impedance (Ri)	mΩ	≤85	Upon fully charge at 1kHz	*
High Rate Discharge (5.0C)	min	N/A	Standard Charge/rest 30min discharge at 5.0C to1.6V/pack	*
Low Temperature Discharge	min	≥240	Standard Charge, Storage:24hrs at 0±2℃ 0.2C discharge at 0±2℃	1.0V/cell Cut-off
Overcharge	N/A	No conspicuous deformation and/or leakage	0.1C charge for 48hrs	*
Charge Retention	min	≥180min	Standard charge Storage: 28 days Standard discharge (0.2C)	1.0V/cell Cut-off
IEC Cycle Life Test	Cycle	≥500	IEC61951-2 ED3.0	*
Humidity	N/A	No leakage	Standard charged, stand for 14 days at $33\pm3^{\circ}$ C and $80\pm5\%$ of relative humidity	*

5.

External Short Circuit	N/A	No fire and no explosion	After standard charge, short-circuit the cell at 20 $^{\circ}$ C \pm 5 $^{\circ}$ C until the cell temperature returns to ambient temperature.(cross section of the wire or connector should be more than 0.75mm ²)	*
Safety Device Operation	N/A	No explosion	Forced discharge at 0.2C to a final voltage of 0V,then the current be increased to 1C and forced discharge continue for 60 min	Leakage of electrolyte and Deformation are acceptable
Free falling(drop)	N/A	∆V<0.02V/cell ∆Ri<5%/cell	Charge at 0.1C for 16hrs,and then leave for 24hrs,check battery before / after drop Height: 50 cm Thickness of wooden board: 30mm Direction is not specified Test for 3 times	*

Notes:

1.

Ta: Ambient Temperature

2.

Approximate charge time from discharged state, for reference only.

3.

Please activate the battery once every 3 months according to the following method. Otherwise, may cause

the battery capacity attenuation, reducing the battery service life and so on.

Charge at 0.1C for 16 hrs, rest 10 min, then discharge with 0.2C to 1.0V/cell,rest 10 min, then charge at 0.2C to 150min.

PRECAUTIONS TO ENSURE THE SAFETY ON BANDING BATTERY

1.

6.

Batteries should be charged prior to use.

2.

.When using a new battery for the first time or after long term storage, please fully charge the battery before

use.

3.

For charging methods please reference to our technical handbook.

4.

Use the correct charger for Ni-Cd or Ni-MH batteries.

5.

Do not reverse charge batteries.

6.

Do not short circuit batteries, permanent damage to batteries may result.

7.

Do not incinerate or mutilate batteries, may burst or release toxic material.

8.

Do not solder directly to cells or batteries.

9.

Do not subject batteries to adverse condition such as extreme temperature, deep cycling and excessive

overcharge/overdischarge.

10.

Store batteries in a cool dry place.

11.

Do not mix batteries with other battery brands or batteries of a different chemistry such as alkaline

and zinc carbon.

12.

Do not mix new batteries in use with semi-used batteries, overdischarge may occur.

13.

Avoid batteries being used in an airtight compartment. Ventilation should be provided inside the battery compartment; otherwise batteries may generate hydrogen gas, which could cause an explosion if exposed to an ignition source.

14.

When connecting a battery pack to a charger, ensure correct polarity.

15.

```
If find any noise, excessive temperature or leakage from a battery, please stop its use.
```

16.

When the battery is hot, please do not touch it and handle it, until it has cooled down.

17.

Do not remove the outer sleeve from a battery pack nor cut into its housing.

18.

When find battery power down during use, please switch off the device to avoid overdischarge.

19.

When not using a battery, disconnect it from the device.

20.

Unplug a battery by holding the connector itself and not by pulling at its cord.

21.

After use, if the battery is hot, before recharging it, allow it to cool in a well-ventilated place out of direct sunlight.

22.

Never put a battery into water or seawater.

23.

During long term storage, battery should be charged and discharged once every 3 months.

24.

Do not attempt to take batteries apart or subject them to pressure or impact. Heat may be generated or fire may result. The alkaline electrolyte is harmful to eyes and skin, and it may damage clothing upon contact.

25.

Keep away from children. If swallowed, contact a physician at once.

26.

Battery failure, may not be thrown away, please recycling

27

Storaged or transport, please let the battery apart and fixed, to prevent external short circuit

7. : IEC61951-2 ED3.0

1	0.1C _t A for 16 h	None	$\begin{array}{c} 0.25 \ C_t A \ for \ 2 \ h \ 20 \ min^{2)} \\ 0.25 \ C_t A \ for \ 2 \ h \ 20 \ min^{2)} \\ 0.25 \ C_t A \ for \ 2 \ h \ 20 \ min^{2)} \\ 0.25 \ C_t A \ to \ 1.0 V \\ 0.2 \ C_5 A \ to \ 1.0 V^{1)} \end{array}$		
2 to 48	0.25 C _t A for 3 h 10 min	None			
49	0.25 C _t A for 3 h 10 min	None			
50	0.1 C _t A for 16 h	1h to 4h			
● 100,150,200,250,300,350,400and 450 周. ●					

Append: IEC61951-2 ED3.0 Endurance in cycles

Before the endurance in cycles test, the cell shall be discharged at 0.2 1 A to a final voltage of 1.0V/sell. The following endurance test shall then be carried out, irrespective of cell designation, in an ambient temperature of $20^{\circ}C \pm 5^{\circ}C$. Charge and discharge shall be carried out at constant current throughout, using the conditions specified in table 5. Precautions shall be taken to prevent the cell-case temperature from rising above $35^{\circ}C$ during the test, by providing a forced air draught if necessary.

NOTE-Actual cell temperature, not the ambient temperature, determines cell performance.

Cycle number	Charge	Stand in Charged condition	Discharge	
1	0.1C _t A for 16 h	None	0.25 C _t A for 2 h 20 min ²⁾	
2 to 48	0.25 C _t A for 3 h 10 min	None	0.25 C _t A for 2 h 20 min ²⁾	
49	0.25 C _t A for 3 h 10 min	None	0.25 C _t A to 1.0V/cell	
50	0.1 C _t A for 16 h	1h to 4h	0.2C ₅ A to 1.0V/cell	
• It is permissible to allow sufficient open-circuit rest time after the completion of discharge at cycle				

Table 5-Endurance in cycles

 It is permissible to allow sufficient open-circuit rest time after the completion of discharge at cycle 50, so as to start cycle 51 at an exact two-week internal. A similar procedure may be adopted at cycles 100,150,200,250,300,350,400and 450.

• If cell discharge voltage drops below 1.0V/cell,discharge may be discontinued.

Cycles 1 to 50 shall be repeated until the discharge duration on any 50th cycle becomes less than 3h at this stage, a further cycle as specified for cycle 50 shall be carried out.

The endurance test is considered complete when two such successive cycles give a discharge duration less than 3h.The number of cycles obtained when the test is completed shall be not less than 500.

