



# **Specification Approval Sheet**

Name: Polymer Lithium-Ion Battery Model: Akyga LP16350 SPEC: 3.7 / 650mAh



### 1 Scope/

This specification is applies to describe the related Battery product in this Specification and the Battery/cell supplied by Akyga Battery.

## 2 Model/ 16350

# 3 Cell Specification/

No.	Items/	Specifications/		Remark
1	Nominal Capacity	650mAh		0.5C Standard discharge
2	Minimum Capacity	630mAh		
3	Nominal Voltage	3.7V		Mean Operation Voltage
4	Delivery voltage	3.70~3.9V		Within 10 days from Factory
5	Charge Voltage	4.2V±0.03V		By standard charge method
6	Standard charging method	0.2C constant current,4.2V constant voltage charge to 4.2V,continue charging till current decline to ≤0.01C		
	Charge current	0.2C	130mA	Standard charge, charge time about 6h(Ref)
7	-	0.5C	325mA	Rapid Charge, charge time about: 3h(Ref)
8	Standard discharging method	0.2C constant current discharge to3.0V,		
9	Cell Internal Impedance	≪80mΩ		Internal resistance measured at AC 1KH <sub>z</sub> after 50% charge



No.	Items/	Specifica	tions/	Remark
10	Maximum charge current	1C	650mA	For continuous charging mod
11	Maximum discharge current	3A	ЗA	For continuous discharge mod
	Operation Temperature and relative	Charge/	0~45℃ 60±25%R.H.	Charge at a very low temperature such a blew 0℃,will be get a lower capacity and
12	humidity Range	Discharge/	-20~60℃ 60±25%R.H.	reduce cycle life of the battery
13	Storage temperature for a long time	-20~25℃ 60±25%R.H.		Do not storage exceed half year. Mu charge once when storage for half yea must charge the battery which with prote circuit when storage for three months.



### 4 Battery/Cell performance test Criteria/

# 4.1 Appearance inspection by visual/

There shall be no such defect as rust, leakage, which may adversely affect commercial value of battery.

### 4.2 Environmental test condition/

Unless otherwise specified, all test stated in this product specification are conduct at below test condition

Temperature: 20°C~25°C

Relative Humidity:60% $\pm$ 25% R.H.

# 4.3 Cell Electrical characteristics/

No	Items/	Test Method and Condition/	Criteria/
1	Rated Capacity at 0.2C(Min.)	After standard charge, the capacity shall be measured on 0.2C discharge till the voltage discharge to3.0V,	≥650mAh
2	Cycle Life	Charging and discharging battery as blew conditions 0.2C standard charge to 4.2V end-off 0.2C standard discharge to 3.0V cut-off Continuous charge and discharge for 300 cycles ,the capacity will be measure after the300 <sup>th</sup> cycle	≥80% of initial capacity
3	Capacity retention	The battery to be charge in accordance with standard charge condition at $20~25^{\circ}$ , then storage the battery at an ambient temperature $20~25^{\circ}$ C for 28 days. Measure the capacity after 30 days with 0.2C at $20~25^{\circ}$ C as retention capacity	Retention capacity ≥85%



calculated.	4	Temperature Dependence of discharge capacity	Cells shall be charged per 3.3.1 and discharged @0.2 C <sub>5</sub> A to 3.0 volts. Except to be discharged at temperatures per Table 3. Cells shall be stored for 3 hours at the test temperature prior to discharging and then shall be discharged at the test temperature. The capacity of a cell at each temperature shall be compared to the capacity achieved at 23 °C and the percentage shall be calculated.	Each cell shall meet or exceed the requirements of Table 3	
-------------	---	---	---	--	--

## Table 3

	1			1	
Discharge Temperature	<b>-20</b> °C	<b>-10</b> ℃	<b>0</b> °C	<b>23</b> ℃	<b>60</b> ℃
Discharge Capacity $(0.2 C_5 A)$	40%	50%	80%	100%	95%

# 4.4 Mechanical characteristics/

No	Items/	Test Method and Condition/	Criteria/
1	Free fall test	The battery to be fully charged in accordance with standard charge condition, then drop the battery three times from a height of 1,0 m onto a concrete floor. The batteries are dropped so as to obtain impacts in random orientations.	No Fire,
2	Vibration test	After standard charging, fixed the cell to vibration table and subjected to vibration cycling that the frequency is to be varied at the rate of 1Hz per minute between 10Hz and 55Hz, the excursion of the vibration is 1.6mm. The cell shall be vibrated for 30 minutes per axis of XYZ axes.	No explosion ,No leakage, No fire




Specification Approval sheet

# 4.5 Safety performance/

No	Items/	Test Method and Condition/	Criteria/
1	Thermal exposure test	Each fully charged cell, stabilized at room temperature, is placed in a circulating air-convection oven. The oven temperature is raised at a rate of 5 °C/min $\pm$ 2 °C/min to a temperature of 130 °C $\pm$ 2 °C. The cell remains at this temperature for 10 min before the test is discontinued.	No explosion, No fire
2	Short test (20℃)	The fully charged battery is to be short-circuited by connecting the positive and negative terminals of the battery with resistance load not exceed 100m $\Omega$ .Tests are to be conducted at room temperature 20~25°C.	No explosion, No fire The Temperature of the Battery surface not exceeded than 150℃
3	Short test (60℃)	The fully charged battery is to be short-circuited by connecting the positive and negative terminals of the battery with resistance load not exceed 100m $\Omega$ .Tests are to be conducted at room temperature about 60-65 °C	No explosion, No fire The Temperature of the Battery surface not exceeded than 150℃
4	Forced discharge test	A discharged cell is subjected to a reverse charge at 1c for 90 min.	No explosion, No fire
5	Over charge test	After standard charge, continue to charge with a constant voltage 3C/4.6V per a cell, holding 8h.	No explosion, No fire



# 5 Cell initial Dimensions/



NO	Items	Units: mm
1	diameter/ (D)	≦16.2mm
2	Height/ (H)	≦35.3mm



Specification Approval sheet

### 6 CAUTIONS IN USE

To ensure proper use of the battery please read the manual carefully before using it.

- . Handling
  - Do not expose to, dispose of the battery in fire.
  - Do not put the battery in a charger or equipment with wrong terminals connected.
  - Avoid shorting the battery
  - Avoid excessive physical shock or vibration.
  - Do not disassemble or deform the battery.
  - Do not immerse in water.
  - Do not use the battery mixed with other different make, type, or model batteries.
  - Keep out of the reach of children.

. charge and discharge Battery must be charged in appropriate charger only.

- Never use a modified or damaged charger.
- Do not leave battery in charger over 24 hours.
- . storage( ): Store the battery in a cool, dry and well-ventilated area.

#### . disposal

• Regulations vary for different countries. Dispose of in accordance with local regulations.

#### 7 Period of Warranty/

The period of warranty is one year from the date of shipment. Akygaguarantees to give a replacement in case of cells with defects proven due to manufacturing process instead of the customer abuse and misuse.

### 8 Storage of the Batteries/

The batteries should be stored at room temperature, charged to about 30% to 50% of capacity. We recommend that batteries be charged about once per half a year to prevent over discharge.

#### 9 Other The Chemical Reaction/

Because batteries utilize a chemical reaction, battery performance will deteriorate over time even if stored for a long period of time without being used. In addition, if the various usage conditions such as charge, discharge, ambient temperature, etc. are not maintained within the specified ranges the life expectancy of the battery may be shortened or the device in which the battery is used may be damaged by electrolyte leakage. If the batteries cannot maintain a charge for long periods of time, even when they are charged correctly, this may indicate it is time to change the battery.

#### 10 Note/

Any other items which are not covered in this specification shall be agreed by both parties.