
# **Type EWT-PP split-flex®**



### **PRODUCT INFORMATION**

The EWT-PP cable protection conduits are made of specially modified polypropylene. The material is phosphor and cadmiumfree. For static applications involving light to medium mechanical loads. The EWT-PP cable protection conduits con-

sist of a two-piece slotted corrugated tube

CDE		
SPE	 Ι.ΔΙ	IONS

onduits are propylene. admium- lving light to onduits con- gated tube	<ul> <li>system and feature the following advantages:</li> <li>Corrugated tubes can be opened and closed at any time.</li> <li>Mounting of pre-assembled cables</li> <li>Retrofitting or repair in mechanical and plant engineering</li> </ul>				In conformity with IEC EN 61386 > 700 N			
				RoHS	Made in Germany			
Order No.	Colour	A Ø mm	B Ø mm	R stat. mm	R dyn. mm	Weight kg/100m	Pack m	
83204258	Black	20.60	28.00	130.00	455 00	12 20	50	

#### Suitable for

Туре

Cable protection conduit open

#### **MATERIAL PROPERTIES**

Standard corrugation EWT-PP M25/P21



Mod. Polypropylene

#### **MECHANICAL PROPERTIES**



Crush resistance

Crush resistance: > 700 N; Testing method: In conformity with IEC EN 61386; Test value: M25/P21

### THERMAL PROPERTIES

|--|

#### Temperature / temperature range

-40 – 130 °C transient / short term 150 °C

#### **FIRE BEHAVIOUR**



**Fire classification** V2 self-extinguishing

#### CONFORMITY



RoHS (EC Directive 202/95/EC)



## Type EWT-PP split-flex®

#### **GENERAL INFORMATION**

e in Made in Germany

All details given in our sales material prospectuses and catalogues as well as the information available online are based on our current knowledge of the products described.

The electronic data and files made available by Murrplastik, particularly CAD files are based on our current knowledge of the product described.

A legally binding assurance of certain properties or the suitability for a certain purpose can not be determined from this information.

All information with respect to the chemical and physical properties of Murrplastik products as well as application advice given verbally, in writing or by tests, is given to the best of our knowledge.

This does not free the purchaser of carrying out their own inspections and tests in order to determine the suitability of a product for a specific purpose.

Murrplastik accepts no responsibility for the available information being up-to-date, correct or complete. Neither do we accept responsibility for the quality of this information.

Murrplastik accepts no liability for damage caused as a result of using our products.

Murrplastik reserves the right to make technical changes and improvements through constant further development of products and services.

Our General Terms and Conditions apply.