


## **Typ UHF**





#### PRODUCT INFORMATION

The UHF holder is made of specially modified polyamide. The material is halogen, phosphor and cadmium-free. The holder is used as a quick and easy connection between control cabinet and door.

The UHF holder features the following advantages:


- Various fastening possibilities
- Protective conduits can still be rotated in the holder

- Pre-assembly of lower part possible
- High tensile strength thanks to double webs
- Suitable for all Murrflex corrugated conduit profiles.
- Bracket is included in delivery

#### Specification:

- EN 45545-2 3x HL3
- NFPA 130: ASTM E 162, ASTM E 662

#### **SPECIFICATIONS**













Туре	Order No.	Colour	Suitable for Murrflex	G Suitable for	A mm	B mm	<b>C</b> mm	D mm	A1 mm	A2 mm	C1 mm	MOQ qty.
suitable for Murrflex EW and EWX												
UHF 36	83621616	Grey	M40/P36(S)	M6	61.00	55.00	60.00	19.00	30.50	24.50	47.50	50

#### **MATERIAL PROPERTIES**



UL listed material mod. polyamide PA 6

#### **THERMAL PROPERTIES**



#### Temperature / temperature range

-40 - 110 °C short term 140 °C

#### **FIRE PROPERTIES**



#### Fire classification

acc. to UL94 V0 self-extinguishing



## Fire properties as per EN 45545-2

C.I.T. R22 / R23 HL3 = 00:43 LOI R22 / R23 HL3 = 33,8 % Ds (max.) R22 / R23 HL3 = 63

ASTM E 162, ASTM E 662 1

#### **TECHNICAL INFORMATION**



Halogen-free



# **Typ UHF**

#### **CONFORMITY**



RoHS (EC Directive 2011/65/EU)

### **APPROVALS AND OPERATING PERMITS**



**EU** railway approval

EN 45545-2 R22/R23 3x HL3



cURus approval



**Made in Germany** 

All details given in our sales brochures and catalogues, as well as the information available online, are based on our current knowledge of the products described.

The electronic data and files made available by Murrplastik, particularly CAD files are based on our current knowledge of the product described.

A legally binding assurance of certain properties or the suitability for a certain purpose can not be determined from this information.

All information with respect to the chemical and physical properties of Murrplastik products, as well as application advice given verbally, in writing or by tests, is given to the best of our knowledge.

They do not release the buyer from the obligation to carry out his own tests and trials in order to determine the concrete suitability of the products for the intended purpose.

Murrplastik accepts no responsibility for the available information being up-to-date, correct or complete. Neither do we accept responsibility for the quality of this information.

Murrplastik accepts no liability for damage caused as a result of using our products.

Murrplastik reserves the right to make technical changes and improvements through constant further development of products and services.